## conferenceseriescom

Seon-yeong Park et al., J Community Med Health Educ 2018, Vol 8 DOI: 10.4172/2161-0711-C1-032

3rd World Congress on

## PILINE NURDN

February 26-28, 2018 London, UK

## FEASIBILITY STUDY ON MICRO-POLYETHYLENE DEGRADABILITY BY MIXED MICROBIAL CONSORTIUM ISOLATED FROM A LANDFILL SITE

Seon-yeong Parkand Chang-gyun Kina Inha University, Korea

ue to increasing use and disposal of plastics or micro-bead, micro-plastics (MPs) contamination threatens the aquatic and marine ecosystem. MPs can e ect on cell viability, cell morphological change, or cause endocrine hormone disturbance phenomena. ey can also migrate long distance by local wind or ocean current, adsorbing persistent organic pollutants, heavy metals and extraneous cell on their surface that can adverse e ect on aboriginal organisms. While recent studies focused or the distribution and ecological e ect of these pollutants, there is still a comparative lack of knowledge about their biological decomposition mechanism and biodegradability. In this study, the biodegradability of polyethylene (PE) has been investigated by using the mesophilic mixed microbial consortium isolated from the practical land II site in Incheon, Korea. PE is dominant type of polymer component of MPs. PE (H(CHH2)nH) with a medium density of 0.94 g/mL (at 25) was purchased from Sigma-Aldrich (USA). PE particles were white and amorphous granular shape sized in the range of approximately 200 to 600 m in a diameter. Mixed microbial consortia were identi ed as Brevibacillus parabrevis and Paenibacillus chitinolyticus. For PE biodegradation test, 1 mL of mixed culture (O.D600=1.2) were inoculated in the 100 mL of freshly autoclaved Basa medium containing 100 mg of PE as the carbon source. e cultivation was carried out at 30 and 150 rpm. e decomposition was analysed through the measurement of weight loss, scanning electron microscope (FE-SEM 4300 SE, Hitachi) and fouritransform infrared spectroscopy (FT-IR, VERTEX 80V, Bruker). A er 60 days of decomposition, dry weight loss of PE was 14.7% and mean particle size decreased from 224.57 m to 175.74 m. From the SEM images, some microbes were strong attached on the PE surfaces verifying that they can have the potential of PE utilization.

## Biography

6 HRQ < HRQJ 3 DUN KDV EHHQ VWXG\LQJ VRLO LPSURYHPHQW DQG ZDWHU UHVRXUFH VWRUDJH WHFKQRO recharge technology of groundwater in the Soil and Groundwater Environment Laboratory at Inha University. She is also studying the environmental impacts and decomposition mechanism of micro pollutants i.e., pharmaceuticals and micro plastics.

cgk@inha.ac.kr

Notes: